

**ROWAD NATIONAL PLASTIC CO. LTD.****Rowad HIPS Sheets**

Typical Properties	Units	Value	ASTM Method
Density	Gm/cc	1.05	D 792
Flammability	HB	1/16"	UL-94
Tensile Strength at Break	Mpa	16	D 638
Elongation at break	%	40	D 638
Tensile Modulus	Mpa	1900	D 638
Flexural Strength	Mpa	116	D 790
Izod Impact Charpy Unnotched	Kj/m ²	No breakage	D 256A
Impact strength Charpy Notched	Kj/m ²	9	D 256A
Vicat Softening Point	°C	110	D 1525
Heat Deflection Temperature	°C	60	D 648
Rockwell Hardness	R-Scale	30	D 785

Features:

Rowad HIPS sheet (RHIPS) is a thermoplastic with elastomer as an additive that gives excellent extrudability, high rigidity and impact strength at low temperatures, high elongation, chemical resistance and resist cracking and splitting. It can also be made more weather resistant and durable for outdoor applications as per customer requirement, by the application of UV layers on both sides.

Applications:

RHIPS has a wide range of applications such as:

1. Refrigerator components
2. House wares and Furniture
3. Molds for Industrial stone
4. General packaging such as jewellery and watches
5. Food Packaging

Colors

RHIPS is available in all custom colors.

Sizes:

Thickness: 2 – 15 mm
Length: Unlimited but normally 3 meters is widely in use
Width: up to 2.05 meters

Resistance to Chemicals:

RHIPS has high chemical resistance

Forming and Fabrication:

RHIPS can be thermoformed, sawed, routed, drilled, etc.

Weatherability:

RHIPS can withstand prolonged periods of exposure to weather and sunlight without yellowness and stress cracking due to the presence of UV stabilizers and protective covers.

Mechanical Properties:

RHIPS has high resistance against cracking and splitting due to high elongation

Rowad National Plastic Co. Ltd.
P.O Box 29452
Riyadh 11457
Kingdom of Saudi Arabia
Tel: +966 1 2651966
Fax: +966 1 2651973
Email: << marketing@alrowad.com.sa>>
Web: << www.alrowad.com.sa>>

Disclaimer Notice: This information is given in good faith and to the best of our knowledge, but without any warranty. Users of our materials should determine the suitability for a specific application. It is always advisable to do preliminary testing. The above data show typical average values only.